




Home

487, price group 2

Combining softness, volume and an undeniable note of elegance, this fabric provides pleasant warmth in the home and hassle-free maintenance, so you can enjoy your furniture to the fullest. With a slight sheen, this chenille fabric offers a subtly refined look and texture that is simply irresistible to the touch. The chunk-dyed color range includes a mix of earthy tones and cozy deep hues that never go out of style



100% Polyester



Martindale: 85.000



Lightfastness: 4-5

PRODUCT CHARACTERISTICS

Product group	chenille flatweave
Applications	sofa's, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Composition upside	n/a
Bonding	sbr
Statistic code	55159130
Dyeing method	piece dyed
Available colours	11


DURABILITY SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	4-5		min. 4	min.5	B-C
	middle colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324, Schedule 4 part 1 Ignition source 0: cigarette.	CTL	passed				

PROCESSING SPECIFICATION

Minimum workable width [cm]	± 138							
Roll length [m]	± 35							
Material weight [g/m]	± 715							
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1,840	685	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	104,2	37,4	min. 25	min. 30	A/B
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel	passed					
	Oeko-Tex, product class II	Centexbel	certified					

CLEANING SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30° C DIN EN	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,2	0,0	n/a	n/a	A/A
				- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.				

All information is based on the data provided by the manufacturer.